

PRODUCT DATA SHEET
SPARTA-FLEX® PURE™ BY HP SPARTACOTE®



US Patents: 6.833,424 & 7,169,876

PRODUCT DATA

Type of Material: Polyaspartic Aliphatic Polyurea

VOC Content: 0 g / L

Recommended Dry Film Thickness: 4 to 8 mils per coat

Shelf Life: 12 months unopened. Store at 40°F to 100°F in a covered area (out of the sun)

Pot Life:* 15 to 20 minutes

Minimum Re-coat:* 2-3 Hours, minimum

Light Foot Traffic:* 2-3 Hours minimum

Maximum Re-coat:* 24 hours (contact manufacturer)

Mixing Ratio:* 1.0 part A; 1.0 part B

Tensile Strength: ASTM D 638: 4,500 to 5,000 psi

Impact Resistance: Direct/Reverse 160/160

Falling Sand Abrasion Resistance ASTM D 968:

Clear.....30 liters sand/1 dry mil

Pigmented.....38 liters sand/1 dry mil

Mandrel Bend, ASTM D 522:

Passes, no cracking, 1/8" mandrel bend

GENERAL INFORMATION

Sparta-Flex *PURE™* is an odorless fast-curing two-part polyaspartic aliphatic polyurea sealer/finish coating for both decorative and protective applications. The material is applied in single or multiple coats by brush, roller or squeegee varying thicknesses to a variety of substrates including concrete and metal. It can be applied as a top coat employed within seamless multi-build chip/quartz seamless flooring systems. Important characteristics of Sparta-Flex *PURE™* are its rapid-cure capabilities, tremendous bond strength, UV resistance and excellent color/gloss retention.

Sparta-Flex *PURE™* provides excellent impact, abrasion, and chemical resistance characteristics. Suitable for high traffic interior or exterior applications, the material is ideal for clear topcoat sealer applications over decorative concrete, walkways, commercial applications, industrial facilities, swimming pool decks and garage floors.

FEATURES & BENEFITS

- Walk-on in hours, 24-hour return to service
- No Odor, No VOCs
- Excellent abrasion, impact & wear resistance
- UV-Resistant; retains optical clarity of clear sealer/finish
- Maximum Re-coat time: 48 hours
- Low temperature cure (25°F)
- Excellent chemical & stain resistance, resistant to skydrol
- Resistant to hot-tire pickup
- Micro-Media agents can be introduced as traction additives
- Tolerant to 300°F for random, incidental heat contact
- Meets FDA/CFSAN, U.S. Food Code, physical facilities criteria as outlined in 6.100.11 Surface Characteristics USDA acceptable. Not intended for 21 CFR food contact.

COLORS

Sparta-Flex *PURE™* is available in a water-clear gloss finish as well as all standard HP Spartacote® colors, including safety colors.

COMMON USES

- Multi-coat high traffic commercial and industrial solid color concrete flooring system consisting of multiple pigmented coats and clear top coat(s).
- Multi-coat residential garage floor coating consisting of multi-build simulated granite paint chip or quartz flooring systems.
- Two-coat blasted steel coating application consisting of 1 zinc-rich primer coat followed by one-coat of Sparta-Flex *PURE™*.
- Clear sealer or finish coating over decorative concrete surfaces. Includes acid stained and semi polished concrete, polymer modified overlays and stamped concrete.
- UV-resistant sealer for exterior applications

www.hpspartacote.com

COVERAGE

Mils	4-mils	5-mils	6-mils	7-mils	8-mils	9-mils	10-mils
Sq. Ft Per Coat/Gallon	401	321	267	229	200	178	160

SURFACE PREPARATION

Sparta-Flex *PURE™* is not intended for direct to concrete applications, but rather as an intermediate or top coating in conjunction with other HP Spartacote® products.

Surfaces to be coated must be free of grease and any other contaminants that may impede adhesion. Always check the surface for any bond inhibitors prior to application. Any repairs must be addressed prior to application and should be repaired in accordance with ICRI standards.

APPLICATION

A moisture emission measurement system is necessary to assess the moisture drive of a concrete slab prior to installation of any toppings or coatings. The transmission rate must not exceed three pounds per 1,000 square feet per 24 hours. The relative humidity of the slab must not exceed 80%. If there is a moisture emission situation in excess of the above rate, consult HP Spartacote, Inc. for vapor control flooring application systems. The application process will depend on the system being installed, reference appropriate specification for details.

Sparta-Flex *PURE™* must be stored a room temp and applied at room temp. If the material is too warm, pot-life will be shortened. If the material is too cold, viscosity will increase and make the material difficult to work with. Mix part A and part B in equal parts (1:1) using a clean, dry working vessel. Stir gently, avoid over-mixing or creating a vortex that would introduce moisture. Do not mix below the dew point, which will shorten the pot life. No induction time is required prior to use. If micro-media agents are to be incorporated, they are to be added after thoroughly mixing A and B.

Suggested application thickness is 8 mils or 200 ft per coat, per gallon. Contact HP Spartacote® directly for specifics on effective application techniques. Maximum application mil thickness in a single application is 10-12 mils.

Material will be dry to the touch 2-3 hours after application, dependent on ambient temperature, slab temperature and humidity. Product may be re-coated within 2-24 hours following application. Light foot traffic is acceptable 12-hours following application and vehicular traffic is acceptable 2-3 hours after application.

CLEANUP

Use Xylene or MEK. Do Not use Alcohols.

SAFETY

Polyaspartic aliphatic polyurea products contain chemical ingredients that are considered hazardous. Read the container label warning and Material Safety Data Sheet prior to use.

WARRANTY

HP Spartacote® warrants that this product will be within consistent quality and manufactured in accordance with manufacturer's specifications. Given that the manufacturer holds no control over the use, HP Spartacote® does not warranty the installation Sparta-Flex®. Manufacturer's warranty shall be limited to the refunding of any materials determined to be defective.

Sparta-Flex *PURE™* Product Data Sheet
© 2011 HP Spartacote, Inc.